

Test Report

Number: GZHH00178416

Applicant: GUANGDONG GUANG MING FA PLASTIC CO., LTD
LIANSHANG INDUSTRIAL PARK, CHENGHAI,
SHANTOU CITY, GUANGDONG PROVINCE,
515833, CHINA.

Date: Jul 07, 2015

Attn: WEIMIN WANG

Sample Description:

One (1) set of submitted sample said to be :

Item Name : **Cazuelita Mini PS Oval Con Tapa + Mix Chucharita/Tenedor 11.5x7x6.5cm**
Item No. : **B920006 (B920004/ B920005/ B920007/ B920008/ B920009/ B920010/
B920011/ B920015/ B920016/ B920017/ B920018/ B920019)**
P. O. No. : SP15001220
Vendor : Guangdong Guang Ming Fa Plastic Co., Ltd
Buyer : Soler Hispania S.L.
Country of Origin : China

Tested sample




Tests conducted:

As requested by the applicant, refer to attached page(s) for details.

To be continued

Authorized by:
For Intertek Testing Services Shenzhen Ltd.
Guangzhou Branch, Hardlines



Ben N.L. Lin
General Manager



Page 1 of 5



Test Report

Number: GZHH00178416

Conclusion:

Tested Sample
Tested component(s) of
submitted sample


Standard
European Commission Regulation No. 10/2011 and
Regulation 1935/2004 on overall migration

European Commission Regulation No. 10/2011 Annex II
and Regulation 1935/2004 on specific migration of heavy
metal content

Result
Pass

Pass

Authorized by:
For Intertek Testing Services Shenzhen Ltd.
Guangzhou Branch, Hardlines



Ben N.L. Lin
General Manager



Page 2 of 5

Test Report

Number: GZHH00178416

Tests Conducted

1 Overall Migration Test

As per Commission Regulation (EU) No. 10/2011 and its amendments.

I. Test condition:

Aqueous food simulant:

Test no.
OM3

Time and temperature
2 hours at 70 °C

Fatty food simulant:

Test no.
OM3

Time and temperature
2 hours at 70 °C

<u>Food Simulant</u>	<u>Temperature(°C)</u>	<u>Time (hours)</u>
3% (w/v) acetic acid	70	2
10% (v/v) ethanol	70	2
Substitute simulant 95%(v/v) ethanol	60	4
Substitute simulant iso –octane	40	0.5

II. Test Results :

<u>Food Simulant</u>	<u>Result (mg/dm²)</u>	<u>Limit (mg/dm²)</u>
3% (w/v) acetic acid	<1	10
10% (v/v) ethanol	<1	10
Substitute simulant 95%(v/v) ethanol	<1	10
Substitute simulant iso –octane	<1	10

Tested component : Transparent PS plastic (lid)

Remark : Ratio of food contact surface area to volume used to establish the compliance of material or article = 1 dm² : 100mL.

Date sample received : Jun 24, 2015

Testing period : Jun 24, 2015 to Jul 01, 2015

2 Specific Migration of Heavy Metal

As per Commission Regulation (EU) No. 10/2011 and its amendments

I. Test condition:

Temperature : 70 °C

Time : 2hours





Test Report

Number: GZHH00178416

Tests Conducted

II. Test result :

<u>Food Simulant</u>	<u>Element</u>	<u>Result (mg/kg)</u>	<u>Limit (mg/kg)</u>
3% (w/v) Acetic acid in aqueous solution	Barium	<0.1	1 (max.)
	Cobalt	<0.03	0.05 (max.)
	Copper	<1	5 (max.)
	Iron	<5	48 (max.)
	Lithium	<0.1	0.6 (max.)
	Manganese	<0.1	0.6 (max.)
	Zinc	<5	25 (max.)

Tested components : Transparent PS plastic (lid)

Date sample received : Jun 24, 2015

Testing period : Jun 24, 2015 to Jul 01, 2015



Test Report

Number: GZHH00178416

Tests Conducted

Submitted sample



End of report

This report is made solely on the basis of your instructions and/or information and materials supplied by you. It is not intended to be a recommendation for any particular course of action. Intertek does not accept a duty of care or any other responsibility to any person other than the Client in respect of this report and only accepts liability to the Client insofar as is expressly contained in the terms and conditions governing Intertek's provision of services to you. Intertek makes no warranties or representations either express or implied with respect to this report save as provided for in those terms and conditions. We have aimed to conduct the Review on a diligent and careful basis and we do not accept any liability to you for any loss arising out of or in connection with this report, in contract, tort, by statute or otherwise, except in the event of our gross negligence or wilful misconduct.



Page 5 of 5